

United States Patent [19]

Brady et al.

[11] 4,436,797

[45] Mar. 13, 1984

[54] X-RAY MASK

[75] Inventors: Michael J. Brady, Brewster; Bernard S. Meyerson, Yorktown Heights, both of N.Y.; John M. Warlaumont, Ridgewood, N.J.

[73] Assignee: International Business Machines Corporation, Armonk, N.Y.

[21] Appl. No.: 394,018

[22] Filed: Jun. 30, 1982

[51] Int. Cl.³ F24F 13/00; B05B 5/00; C23C 15/00; B32B 9/00

[52] U.S. Cl. 430/5; 428/408; 428/446; 428/426; 427/65; 427/160; 204/192 C; 204/192 SP; 204/192 E; 430/967

[58] Field of Search 428/408, 446; 427/65, 427/160; 204/192 C, 192 SP, 192 E; 430/5

[56] References Cited

U.S. PATENT DOCUMENTS

3,577,325	5/1971	Fairchild	428/408
3,742,230	6/1973	Spears et al.	250/65 R
3,824,100	7/1974	Griest	430/5
3,925,677	12/1975	Fraser	250/505
4,037,111	7/1977	Coquin et al.	250/505
4,060,660	11/1977	Carlson et al.	428/408
4,198,263	4/1980	Matsuda	156/639
4,218,503	8/1980	Reekstin et al.	428/195
4,260,670	4/1981	Burns	430/5
4,301,237	11/1981	Burns	340/394

OTHER PUBLICATIONS

"Spin Resonance Spectroscopy of Amorphous Carbon Films," by R. J. Gambino and J. A. Thompson, Solid State Communications, 34, 15-18, (1980).

"The Growth Kinetics and Properties of Hard and Insulating Carbonaceous Films Grown in an R. F. Discharge," by S. M. Ojha, H. Norstrom and D. McCulluch, Thin Solid Films, 60, 213-225, (1979).

"Mask Technology," by A. Heuberger, Part 3 of Present Status and Problems of X-Ray Lithography, in Advances in Solid State Physics, edited by J. Treusch,

265-274, (Friedr. Vieweg & Sohn, Wiesbaden, W. Ger., 1980).

"Dielectric Properties of Some Thin Organic Polymer Films," by Bernard G. Carbajal, III, Trans. of the Metallurgical Soc. of AIME, 236, 364-369, (1966).

"Insulator Thin Films Formed by Glow Discharge and Radiation Techniques," by A. M. Mearns, Thin Solid Films, 3, 201-228, (1969).

"The Electrical and Optical Properties of Amorphous Carbon Prepared by the Glow Discharge Technique," by D. A. Anderson, Philosophical Magazine, 35, 17-26, (1977).

"Preparation and Characterization of Hydrogenated Amorphous Carbon Films: Electrical and Optical Properties," PhD Thesis by Bernard S. Meyerson, City University of New York, 1-117, (1980).

"The Rearrangement of Acetylene, Benzene, Ethane, Ethylene, Methane and Naphthalene in a Microwave Discharge," by F. J. Vastola and J. P. Wightman, J. Appl. Chem., 14, 69-73, (1964).

"Deposition of Hard and Insulating Carbonaceous Films on an r.f. Target in a Butane Plasma," by L. Holland and S. M. Ojha, Thin Solid Films, 38, L17-L19, (1976).

Primary Examiner—P. Ives

Attorney, Agent, or Firm—Ronald L. Drumheller

[57]

ABSTRACT

An improved X-ray lithography mask has been fabricated by forming an X-ray absorbing lithography pattern on a supporting foil of hydrogenated amorphous carbon. The substrate foil is formed by depositing a carbon film in the presence of hydrogen onto a surface having a temperature below 375° C. The hydrogen concentration is maintained sufficiently high that the resulting film has at least one atom percent of hydrogen. A film having about 20 atom percent of hydrogen is preferred. While impurities are permitted, impurities must be maintained at a level such that the optical bandgap of the resulting film is at least one electron volt. A film with an optical bandgap of about 2 electron volts is preferred.

20 Claims, 7 Drawing Figures

